


1-800-383-7323 USA/CAN www.energizer.com


ENERGIZER 394/380





DESIGNED FOR USE ON CONTINUOUS LOW DRAIN HIGH PULSE ON DEMAND

Typical Discharge Characteristics



Typical Performance at 21°C (70°F)



SILVER OXIDE

Specifications

Silver Oxide (Zn/Ag₂O)


Nominal Voltage: Typical Capacity: Capacity Test: Typical Weight: Typical Volume: Impedance (40 Hz):

Chemical System:

1.55 Volts 63 mAh* (to 1.2 volts)


63 mAn^a (to 1.2 voits)
15K ohm continuous drain at 21°C
1.1 grams (0.039 oz.)
0.25 cubic centimeters (0.015 cubic inch)
7 to 17 ohms

* Varies according to the applied load, temperature, and cutoff voltage.



Temperature Characteristics

Typical Performance at Low Discharge Rates



Important Notice

This datasheet contains typical information specific to products manufactured at the time of its publication. ©Energizer Holdings, Inc. - Contents herein do not constitute a warranty.